



# Agricultural Concrete Requirements



The minimum concrete requirements for agricultural concrete projects are based primarily upon the following standards and codes:

- Ontario Building Code
- National Farm Building Code of Canada
- CSA A23.1 – Concrete Materials and Methods of Concrete Construction
- Nutrient Management Act, 2002
- NSTS – 04: Concrete, Steel or Equivalent Storage Facilities



While all of these standards make specific references to concrete construction requirements, the most stringent requirements are included in both CSA A23.1 & NSTS – 04 as follows:

CONCRETE APPLICATION	CLASS OF CONCRETE	MAXIMUM W/CM	MINIMUM 28 Day STRENGTH	AIR ENTRAINMENT CATEGORY	REFERENCES
Structurally reinforced concrete exposed to severe manure and/or silage gases, with or without freeze-thaw exposure. Examples: reinforced beams, slabs and columns over manure pits and silos, canals, pig slats, access holes, enclosed chambers, and pipes partially filled with effluents.	<b>A – 1</b>	<b>0.40</b>	<b>35 MPa</b>	<b>1</b>	CSA A23.1 NSTS – 04
Structurally reinforced concrete exposed to moderate to severe manure and/or silage gases and liquids, with or without freeze-thaw exposure. Examples: reinforced walls in exterior manure tanks, silos and feed bunkers, and exterior slabs.	<b>A – 2</b>	<b>0.45</b>	<b>32 MPa</b>	<b>1</b>	CSA A23.1 NSTS – 04
Structurally reinforced concrete exposed to moderate to severe manure and/or silage gases and liquids, with or without freeze-thaw exposure in a continuously submerged condition. Examples: interior gutter walls, beams, slabs and columns, and sewage pipes that are continuously full.	<b>A – 3</b>	<b>0.50</b>	<b>30 MPa</b>	<b>1</b>	CSA A23.1 NSTS – 04
Non-Structurally reinforced concrete exposed to moderate manure and/or silage gases and liquids, without freeze thaw exposure. Examples: interior slabs on grade.	<b>A – 4</b>	<b>0.55</b>	<b>25 MPa</b>	<b>1</b>	CSA A23.1 NSTS – 04
Plain unreinforced concrete not in contact with manure or manure gases. Examples: footings, interior walls, beams, columns and slabs not exposed to agricultural waste.	<b>N</b>	<b>0.55</b>	<b>25 MPa</b>	<b>-</b>	NSTS – 04

## Requirements for the Air Content Categories

CSA A23.1 – Table 4

Air content category	Range in air content* for concretes with indicated nominal maximum sizes of coarse aggregate, %		
	10 mm	14-20 mm	28-40 mm
1	6-9	5-8	4-7
2	5-8	4-7	3-6

\*At the point of discharge from the delivery equipment, unless otherwise specified.

**Note:** Air contents measured after pumping or slip forming may be significantly lower than those measured at the end of the chute.



**NSTS – 04** Concrete, Steel or Equivalent Storage Facilities also includes the following requirements that are critical to concrete agricultural projects in Ontario:

- 6.4.1 The minimum thickness of all concrete floor slabs on grade in permanent liquid nutrient storage facilities should be **125 mm** or as required satisfying the concrete cover requirements.
- 6.4.4.1 Cracking should be controlled by the proper use and construction of control joints, expansion joints, and isolation joints as specified by the engineer.
- 10.2 Concrete Materials – All materials used to make concrete and methods of concrete production and construction should conform to CSA A23.1 and the concrete producer should have a valid **“Certificate of Ready Mixed Concrete Production Facilities”** as issued by the Ready Mixed Concrete Association of Ontario.
- 10.4 Air Entrainment – as per Table 4, CSA A23.1 (Note: NSTS-04 Specifies Air Content Category 1 for all concrete exposure conditions)

- 10.5 Admixtures – Products for concrete mix enhancement such as high-performance concrete, fly-ash and chemical admixtures may be used to improve the structural design and performance. Chemical admixtures should meet the requirements of CSA A23.1. Note: The use of water-reducing admixtures is recommended to improve workability and the overall performance of the concrete.



Photo courtesy of CAC

With permission of Canadian Standards Association, material is reproduced from CSA Standard, A23.1-04/A23.2-04, Concrete Materials and Methods of Concrete Construction/Methods of Test and Standard Practices for Concrete, which is copyrighted by Canadian Standards Association, 178 Rexdale Blvd., Toronto, Ontario, M9W 1R3. While the use of this material has been authorized, CSA shall not be responsible for the manner in which the information is presented, nor for any interpretations thereof. For more information on CSA or to purchase standards, please visit our website at [www.shopcsa.ca](http://www.shopcsa.ca) or call 1-800-463-6727.

This publication is intended for general information purposes only. The Ready Mixed Concrete Association of Ontario and the Cement Association of Canada disclaim any and all responsibility and liability for the accuracy and the application of the information contained in this publication to the full extent permitted by law.

No part of this publication may be reproduced in any form, including photocopying or other electronic means, without permission in writing from Ready Mixed Concrete Association of Ontario.

© 2005 RMCAO. All rights reserved. 09/05

References:

- 1 CSA A23.1-04 – Concrete Materials and Methods of Concrete Construction, Canadian Standards Association International
- 2 Ontario Building Code – 1997, Ontario Ministry of Municipal Affairs and Housing – Housing Development and Buildings Branch
- 3 National Farm Building Code of Canada 1995, Canadian Commission on Building and Fire Codes, National Research Council of Canada
- 4 Nutrient Management Act, 2002, Ontario Ministry of Agriculture and Food
- 5 NSTS – 04 , Concrete, Steel or Equivalent Storage Facilities, Ontario Regulation 267/03, Ontario Ministry of Agriculture and Food
- 6 Concrete Manure Storage Structures – Specifications and Standards in Canada, Cement Association of Canada

Supported by



Technical information prepared by

**Ready Mixed Concrete Association of Ontario**  
 365 Brunel Road, Unit #3 • Mississauga, Ontario L4Z 1Z5  
 Tel: 905.507.1122 • Fax: 905.890.8122 • Email: [info@rmcao.org](mailto:info@rmcao.org)

[www.rmcao.org](http://www.rmcao.org)

