







Residential Concrete Requirements



The minimum requirements for residential concrete are outlined in the Ontario Building Code (OBC) and CSA A23.1 - Concrete Materials and Methods of Concrete

Construction. In general, the concrete supplied for residential concrete applications shall conform to shall conform to Table C1 from CSA A438.

CSA A23.1, Clause 8.13.4

Class of concrete	Description of usage	Maximum water/cementing materials (w/cm) ratio	Minimum 28d compressive strength, MPa	Air content, %
R-1 	Footings for walls, columns, fireplaces, and chimneys	0.70	15	3-6
R-2 	Foundation walls, grade beams, piers, etc.	0.70	15	4-7
R-3 	Interior slabs on ground not exposed to freeze – thaw	0.65	20*	—
C-2 	Garage floors and all concrete exposed to freeze – thaw and deicing salts, such as walkways, driveways, patios, steps	0.45	32	5-8

* Note: OBC Clause 9.16.4.2 requires a minimum of 25 MPa strength when damp proofing is not provided. When damp proofing is provided the minimum concrete strength may be reduced to 15 MPa.

Other basic considerations to bear in mind when placing residential concrete include the following:



■ **Maximum Discharge Time** – The maximum time between batching of the concrete at the concrete plant and the complete discharge of the concrete from

the truck is 120 minutes. This time may be extended through the use of a set retarding admixture.

■ **Concrete Placement** – Concrete shall be deposited as close as possible to its final location and in such a way as to avoid cold joints. Handling or moving of concrete in forms by the use of vibrators or the addition of water on the jobsite shall not be allowed.

- **Concrete Placement Rate** – Concrete for walls shall be deposited continuously in approximately equal horizontal lifts not exceeding 1.2 metres in height.
- **Concrete Consolidation** – Each lift of concrete shall be consolidated by the use of a mechanical vibrator inserted at regularly spaced intervals.
- **Concrete Curing and Protection** – Curing shall be provided by one or more of the following curing methods:
 - Ponding or continuous sprinkling
 - Absorptive mat or fabric continually kept wet
 - Damp sand, earth, or similar moist materials
 - Curing compounds
 - Waterproof paper or plastic film
 - Vapour mist bath
 - Forms in contact with the concrete surface
- **Minimum Concrete Curing Period** – R-1, R-2 and R-3 concrete shall be cured for either 3 days at a minimum temperature of 10°C or for the time necessary to reach 40% of the specified 28 day compressive strength. C-2 concrete shall be cured for 7 days at a minimum temperature of 10°C and for the time necessary to reach 70% of the specified 28 day compressive strength.



Photo courtesy of RMCAO



Photo courtesy of CAC



Photo courtesy of RMCAO

References:

- 1 Ontario Building Code – 2006, Ontario Ministry of Municipal Affairs and Housing – Housing Development and Buildings Branch
- 2 CSA A23.1-Concrete Materials & Methods of Concrete Construction

With permission of Canadian Standards Association, material is reproduced from CSA Standard, A23.1-09/A23.2-09, Concrete Materials and Methods of Concrete Construction/Methods of Test and Standard Practices for Concrete, which is copyrighted by Canadian Standards Association, 178 Rexdale Blvd., Toronto, Ontario, M9W 1R3. While the use of this material has been authorized, CSA shall not be responsible for the manner in which the information is presented, nor for any interpretations thereof. For more information on CSA or to purchase standards, please visit our website at www.shopcsa.ca or call 1-800-463-6727.

This publication is intended for general information purposes only. The Ready Mixed Concrete Association of Ontario and the Cement Association of Canada disclaim any and all responsibility and liability for the accuracy and the application of the information contained in this publication to the full extent permitted by law.

No part of this publication may be reproduced in any form, including photocopying or other electronic means, without permission in writing from Ready Mixed Concrete Association of Ontario.

© 2010 RMCAO. All rights reserved. 01/10

Supported by



Technical information prepared by

Ready Mixed Concrete Association of Ontario
365 Brunel Road, Unit #3 • Mississauga, Ontario L4Z 1Z5
Tel: 905.507.1122 • Fax: 905.890.8122 • Email: info@rmcao.org

www.rmcao.org

